B120EC

STANDARD

Resin • Flat-Head • Near-Edge

- Higher heat resistance up to 150°C.
- Excellent chemical and solvent resistance.
- Applicable to a wide range of synthethic materials: PET/PP/PE/PVC films...
- Ricoh's unique coating on the back allows reliable and superior matching qualities with the thermal head.





RIBBON PROPERTIES

- Total ribbon thickness: < 9 μm
- Polyester film thickness: 4,5 μm
- Friction coefficient: < 0,045

- Ink melting point: 97°C
- Tearing resistance: > 200N/mm²
- Transmission density: 0,65 mini

CERTIFICATIONS / DIRECTIVES

- TSCA (Toxic Substances Control Act)
- RoHS
- WEEE
- 2003/11/EC
- 2000/53/EC
- 76/769/EEC
- ISO EN71-3
- BS 5609 Section III
- REACH

For any other request, please feel free to contact sales.ttr@ricoh-industrie.fr







Usage conditions: 5 to 35°C at 30 to 85% of relative humidity.

Storage life: 24 months after slitting day.

<u>Storage conditions:</u> Keep indoor avoiding high temperature (such as beside a heat source), high humidity, direct sun light.



PRINTING PROPERTIES

Maximum printing speed 10 IPS

	Non coated paper	Coated paper	PET	PP	PE
Compatibility	Partial	/	/	/	
Image density	-	1,76	1,60	1,81	2,05

Note: Smoothness Bekk for paper family must be over 2000s.

Image resolution for paper & film:


<u>Minimum size:</u> - For the lines: 0. 1mm - For the caracters: 1.0mm

PRINTED IMAGE DURABILITY

Tests lead with flat head technologie

TESTS	RESULTS	B120	EC with standard n	natt white pa	olyester
Smear + heat (100°C) Smear with carboard (weight 1kg - 50 back & forwards)	ANSI A		Engine oil Brakefluid	8	250
Heat (150°C) Heat gradient 3,6kgF/cm²	No ink on cotton fabric		Windshieldwas	her	250
Scratch 50 back and forwards with a rub tester	ANSI A		Unleaded petro	ol 150	200
Light Xenon lamp at 650W/m²	ANSI A		Ethanol 40	170	
Water 24 hours in water	ANSI A	Ba	ck & forwards until a	beginning of (erase

B120EC DURABILITY



5 : no damage

0 : erased

B120EC with <u>standard</u> white polyester

B120EC with <u>specific</u>* polyester

* dedicated to solvent resistance

August 2017